



impiego

macchina rettilinea su finezza 12-14
ad 1 filo, circolare da 12 a 20 ad 1 filo,
cotton 21-24 ad 1 filo.

estensibilità e restringimento

il grado d'elasticità del capo è determinato
dalla regolazione della tensione del filo e
della fittezza dei punti maglia in fase di
smacchinatura. Si consiglia di eseguire un
capo prototipo e sottoporlo ad un test di
lavaggio.

scarto di lavorazione

la particolare costruzione di quest'articolo
e il processo di tintura comportano uno
scarto del 5-7%.

colori

uniti

solidità

secondo le norme UNI/ISO; per i rigati
con colori contrastanti, è necessario
richiedere solidità specifiche ed eseguire
test di lavaggio.

finissaggio industriale

per scaricare le tensioni di lavorazione
e completare il ritorno elastico della
componente poliammidica, si consiglia
di lavare con ammorbidente specifico
e vaporizzare abbondantemente in
fase di stiro.

servizio campionature fino al 31-12-2016

* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo
e dei bagni ottimali di tintura, vi pre-
ghiamo di richiedere la scheda tecnica.*

use

*flat-knitting machine gauge 12-14 for 1-ply,
circular from 12 to 20 for 1-ply, cotton
21-24 for 1-ply.*

stretch and shrinking degree

*the garment stretch degree is determined by
yarn tension and knit thickness adjustment
during knitting. It is suggested to make a
prototype garment and wash it as a test.*

knitting waste

*the particular yarn construction and dyeing
process may cause a 5-7% knitting waste.*

colours

solid

fastness

*in compliance with UNI/ISO norms; for
striped garments with contrasting colours,
it is recommended to ask for specific
fastness and carry out washing tests.*

industrial finishing

*in order to loosen the knitting tensions
and help the polyamide component stretch
return, it is suggested to wash with specific
softener and steam generously during
ironing.*

sampling service until 31-12-2016

* colours ready for sampling

*for any information regarding the use
and dye-lot sizes of the yarn please ask
for the technical sheet.*

