



87% WV lana Merino extrafine irrestingibile /  
shrink-resistant Merino extrafine wool  
7% PA fibra poliammidica / polyamide fibre  
6% PL poliestere metallizzato / metallized polyester

W  
17  
18

### impiego

macchina rettilinea su finezza 16-14  
a 1 filo, 12 a 2 fili, circolare da 12 a 20  
a 1 filo, cotton 24-27-30 gauge a 1 filo,  
cotton 21 gauge a 2 fili.

**In fase di smacchinatura, porre particolare attenzione alla messa a punto della macchina, per limitare le rotture della piattina di poliestere.**

### colori

moulinè

### scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 3%

### solidità

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

### finissaggio industriale

vaporizzare abbondantemente in fase di stiro; per valorizzare il filato e per eliminare le tensioni di smacchinatura, si consiglia un lavaggio con ammorbidente specifico.

### servizio campionature fino al 31-12-2016

\* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.*

### use

*flat-knitting machine gauge 16-14 for 1-ply, 12 for 2 ply, circular from 12 to 20 for 1-ply, cotton 24-27-30 gauge for 1 ply, cotton 21 gauge for 2-ply.*

***Pay great attention during knitting to the set-up of the machine, in order to limit the polyester breakage.***

### colours

moulinè

### knitting waste

*the particular yarn construction and dyeing process may cause a 3% knitting waste.*

### fastness

*in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.*

### industrial finishing

*steam generously during ironing; in order to enhance the yarn and eliminate the shrinkage due to the knitting tensions, it is suggested to wash with specific softener.*

### sampling service until 31-12-2016

\* colours ready for sampling

*for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.*

