



impiego

macchina rettilinea 5 ad 1 filo, 3 a 2 fili.

colori

uniti, mélange e vigoureux.

solidità

secondo le norme WOOLMARK; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

finissaggio industriale

per ottenere una mano più gonfia, è consigliabile un lavaggio con ammorbidente specifico.

servizio campionature fino al 31-12-2016

* colori pronti per campionatura
colori mélange: Ø96-ØN9-618-5W6-E15-L97
colori uniti: ØØ7-Ø99-ØQ7-5X5

per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.

use

flat-knitting machine gauge 5 for 1-ply, 3 for 2-ply.

colours

solid, mélange and vigoureux colours.

fastness

in compliance with WOOLMARK norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.

industrial finishing

for a more voluminous touch employ an appropriate softener when washing.

sampling service until 31-12-2016

* colours ready for sampling
mélange colours: Ø96-ØN9-618-5W6-E15-L97
solid colours: ØØ7-Ø99-ØQ7-5X5

for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.

