

**Tornado / Tornado TR**

Nm 9500

Nm 9500



by EDUARDO MROGLIO

50% PC fibra poliacrilica / polyacrylic fibre  
 30% PA fibra poliammidica / polyamide fibre  
 14% WM Mohair  
 6% WV lana vergine / new wool

W  
17  
18**impiego**

macchina rettilinea su finezza 7 e 5 a 1 filo

**estensibilità e restringimento**

il grado d'elasticità del capo è determinato dalla regolazione della tensione del filo e della fittezza dei punti maglia in fase di smacchinatura. Si consiglia di eseguire un capo prototipo e sottoporlo ad un test di lavaggio.

**scarto di lavorazione**

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 3%.

**colori**

uniti, mélange.

**solidità**

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

**finissaggio industriale**

per scaricare le tensioni di lavorazione e completare il ritorno elastico della componente poliammidica, si consiglia di lavare con ammorbidente specifico e vaporizzare abbondantemente in fase di stiro.

**Tornado**

tutti i colori sono pronti per campionatura

**Tornado TR****servizio campionature fino al 31-12-2016**

\* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.*

**use***flat-knitting machine gauge 7-5 for 1-ply.***stretch and shrinking degree**

*the garment stretch degree is determined by yarn tension and knit thickness adjustment during knitting. It is suggested to make a prototype garment and wash it as a test.*

**knitting waste**

*the particular yarn construction and dyeing process may cause a 3% knitting waste.*

**colours***solid, mélange.***fastness**

*in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.*

**industrial finishing**

*in order to loosen the knitting tensions and help the polyamide component stretch return, it is suggested to wash with specific softener and steam generously during ironing.*

**Tornado***all colours are ready for sampling***Tornado TR****sampling service until 31-12-2016**

\* colours ready for sampling

*for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.*

