

**impiego**

macchina rettilinea su finezza 3 a 1 filo

colori

uniti, mélange

scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 3%.

solidità

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

finissaggio industriale

vaporizzare abbondantemente in fase di stiro. Per ottenere una mano più gonfia e quindi una maglia più curata, è consigliabile un lavaggio con un minimo di ammorbidente specifico.

tutti i colori sono pronti per campionatura

per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.

use

flat-knitting machine gauge 3 for 1 ply

colours

solid and mélange

knitting waste

the particular yarn construction and dyeing process may cause a 3% knitting waste.

fastness

in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.

industrial finishing

steam generously during ironing. Wash with a minimum dose of appropriate softener for a more voluminous touch and a cleaner feel.

all colours are ready for sampling

for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.

