



impiego

macchina rettilinea su finezza 16-18 a 1 filo, 14 a 1-2 fili, 12 a 2 fili, circolare da 16 a 20 a 1 filo, cotton 24-27-30 a 1 filo.
Con lavorazioni a due o piú fili, si raccomanda di verificare le tensioni in macchina.
Per valutare i cali nei vari punti maglia, é necessario eseguire un capo prototipo e sottoporlo a test di lavaggio.
In fase di smacchinatura, porre particolare attenzione alla messa a punto della macchina, per limitare le rotture del filo di acciaio.

scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 5-7%.

colori
uniti

solidità

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

finissaggio industriale

vaporizzare abbondantemente in fase di stiro; per una mano più fluida e per eliminare le tensioni di smacchinatura, si consiglia un lavaggio con ammorbidente specifico.

servizio campionature fino al 31-12-2017
*** colori pronti per campionatura**

per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.

use

flat-knitting machine gauge 16-18 for 1-ply, 14 for 1-2 ply, gauge 12 for 2 ply, circular from 16 to 20 for 1-ply, cotton 24-27-30 for 1-ply.
For 2 or more ply knitting, it is recommended to check machine tension.
In order to evaluate shrinkage in the different knits, it is suggested to make a prototype garment and wash it as a test.
Pay great attention to the machine set-up during knitting in order to limit steel wire breakage

knitting waste

the particular yarn construction and dyeing process may cause a 5-7% knitting waste.

colours
solid

fastness

in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.

industrial finishing

steam generously during ironing; for a smoother hand and to eliminate the shrinkage due to the knitting tensions, it is suggested to wash with specific softener.

sampling service until 31-12-2017
*** colours ready for sampling**

for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.

•1	bianco	white
•2	chiari	light
•3	medi	medium
•4	scuri	dark
•5	special	special



NO harmful or irritant chemicals used.
NON trattato con sostanze nocive o irritanti.



Safe & healthy working conditions.
Condizioni di lavoro sane e sicure.

