



55% VI viscosa / viscose
34% PA fibra poliammidica / polyamide fibre
6% WO lana fine Merino irrestingibile /
shrink-resistant fine Merino wool
5% WS Cashmere

W
18
19**impiego**

macchina rettilinea su finezza 12-14 ad
1 filo, circolare da 12 a 20 ad 1 filo, cotton
21-24 ad 1 filo.

estensibilità e restringimento

il grado d'elasticità del capo è determinato dalla regolazione della tensione del filo e della fittezza dei punti maglia in fase di smacchinatura. Si consiglia di eseguire un capo prototipo e sottoporlo ad un test di lavaggio.

scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 5-7%.

colori

uniti e mélange

solidità

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

finissaggio industriale

per scaricare le tensioni di lavorazione e completare il ritorno elastico della componente poliammidica, si consiglia di lavare con ammorbidente specifico e vaporizzare abbondantemente in fase di stiro.

servizio campionature fino al 31-12-2017

* colori pronti per campionatura

per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.

use

*flat-knitting machine gauge 12-14 for 1-ply,
circular from 12 to 20 for 1-ply, cotton
21-24 for 1-ply.*

stretch and shrinking degree

the garment stretch degree is determined by yarn tension and knit thickness adjustment during knitting. It is suggested to make a prototype garment and wash it as a test.

knitting waste

the particular yarn construction and dyeing process may cause a 5-7% knitting waste.

colours

solid and mélange

fastness

in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.

industrial finishing

in order to loosen the knitting tensions and help the polyamide component stretch return, it is suggested to wash with specific softener and steam generously during ironing.

sampling service until 31-12-2017

* colours ready for sampling

*for any information regarding the use
and dye-lot sizes of the yarn please ask
for the technical sheet.*

•1	bianco	white
•2	chiari	light
•3	medi	medium
•4	scuri	dark
•5	special	special