

**impiego**

macchina rettilinea su finezza 12-14  
ad 1 filo, circolare da 12 a 20 ad 1 filo,  
cotton 21-24 ad 1 filo.

**estensibilità e restringimento**

il grado d'elasticità del capo è determinato  
dalla regolazione della tensione del filo e  
della fittezza dei punti maglia in fase di  
smacchinatura. Si consiglia di eseguire un  
capo prototipo e sottoporlo ad un test di  
lavaggio.

**scarto di lavorazione**

la particolare costruzione di quest'articolo  
e il processo di tintura comportano uno scarto  
del 5-7%.

**colori**

uniti

**solidità**

secondo le norme UNI/ISO; per i rigati  
con colori contrastanti, è necessario richiedere  
solidità specifiche ed eseguire  
test di lavaggio.

**finissaggio industriale**

per scaricare le tensioni di lavorazione  
e completare il ritorno elastico della  
componente poliestere, si consiglia  
di lavare con ammorbidente specifico  
e vaporizzare abbondantemente in  
fase di stiro.

*per informazioni sull'utilizzo dell'articolo  
e dei bagni ottimali di tintura, vi preghia-  
mo di richiedere la scheda tecnica.*

88% WV lana Merino extrafine irrestingibile /  
shrink-resistant extrafine Merino wool  
12% PL poliestere elasticizzato / stretch polyester

**use**

*flat-knitting machine gauge 12-14 for 1-ply,  
circular from 12 to 20 for 1-ply, cotton  
21-24 for 1-ply.*

**stretch and shrinking degree**

*the garment stretch degree is determined by  
yarn tension and knit thickness adjustment  
during knitting. It is suggested to make a  
prototype garment and wash it as a test.*

**knitting waste**

*the particular yarn construction and dyeing  
process may cause a 5-7% knitting waste.*

**colours**

*solid*

**fastness**

*in compliance with UNI/ISO norms; for striped  
garments with contrasting colours,  
it is recommended to ask for specific fastness  
and carry out washing tests.*

**industrial finishing**

*in order to loosen the knitting tensions  
and help the polyester component stretch  
return, it is suggested to wash with specific  
softener and steam generously during ironing.*

*for any information regarding the use  
and dye-lot sizes of the yarn please ask  
for the technical sheet.*

