



impiego

macchina rettilinea su finezza 5 ad 1 filo,
3 a 2 fili.

colori

uniti e mélange
Non sono riproducibili colori a campione

solidità

secondo le norme UNI/ISO; per i rigati
con colori contrastanti, è necessario
richiedere solidità specifiche ed eseguire
test di lavaggio.

finissaggio industriale

vaporizzare abbondantemente in fase di
stiro. Per ottenere una mano più gonfia e
quindi una maglia più curata, è consigliabile
un lavaggio con un minimo di ammorbiden-
te specifico.

tutti i colori sono pronti per campionatura

*per informazioni sull'utilizzo dell'artico-
lo e dei bagni ottimali di tintura, vi pre-
ghiamo di richiedere la scheda tecnica.*

use

*flat-knitting machine gauge 5 for 1-ply,
3 for 2 ply.*

colours

*solid, mélange
We cannot match colours in this quality.*

fastness

*in compliance with UNI/ISO norms; for
striped garments with contrasting colours,
it is recommended to ask for specific
fastness and carry out washing tests.*

industrial finishing

*steam generously during ironing. Wash with
a minimum dose of appropriate softener for a
more voluminous touch and a cleaner feel.*

all colours are ready for sampling

*for any information regarding the use
and dye-lot sizes of the yarn please ask
for the technical sheet.*

