

E.Miroglio
EAD Cert.N°
SOF0170206
ISO 9001:2008



SAFE &
healthy
working
conditions



NO harmful
or irritant
chemicals
used

impiego

macchina rettilinea su finezza 16 e 14 a 1 filo, cotton
24-27 gauge a 1 filo.

estensibilità e restringimento

il grado d'elasticità del capo è determinato dalla regolazio-
ne della tensione del filo e della fittezza dei punti maglia
in fase di smacchinatura. Si consiglia di eseguire un capo
prototipo e sottoporlo ad un test di lavaggio.

scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di
tintura comportano uno scarto del 5-7%.

colori

uniti

solidità

secondo le norme UNI/ISO; per i rigati con colori contra-
stanti, è necessario richiedere solidità specifiche ed esegui-
re test di lavaggio.

finissaggio industriale

per scaricare le tensioni di lavorazione e completare il ri-
torno elastico della componente poliestere, si consiglia di
lavare con ammorbidente specifico e vaporizzare abbon-
dantemente in fase di stiro.

servizio campionature fino al 30-06-2018

* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo e dei bagni
ottimali di tintura, vi preghiamo di richiedere la
scheda tecnica.*

use

flat-knitting machine gauge 16-14 for 1-ply, cotton
24-27 gauge for 1-ply.

stretch and shrinking degree

the garment stretch degree is determined by yarn tension
and knit thickness adjustment during knitting. It is sug-
gested to make a prototype garment and wash it as a test.

knitting waste

the particular yarn construction and dyeing process may
cause a 5-7% knitting waste.

colours

solid

fastness

in compliance with UNI/ISO norms; for striped garments
with contrasting colours, it is recommended to ask for
specific fastness and carry out washing tests.

industrial finishing

in order to loosen the knitting tensions and help the
polyester component stretch return, it is suggested to
wash with specific softener and steam generously
during ironing.

sampling service until 30-06-2018

* colours ready for sampling

*for any information regarding the use and dye-lot
sizes of the yarn please ask for the technical sheet.*

