

knitted with monofilament Polyester

E.Miroglio
EAD Cert.N°
SOF0170206
ISO 9001:2008SAFE &
healthy
working
conditionsNO harmful
or irritant
chemicals
used**impiego**

macchina rettilinea su finezza 16-18 ad 1 filo, 14 a 1-2 fili, 12 a 2 fili, circolare da 16 a 20 ad 1 filo, cotton 24-27-30 gauge ad 1 filo.

Con lavorazioni a due o più fili, si raccomanda di verificare le tensioni in macchina.

Per valutare i cali nei vari punti maglia, è necessario eseguire un capo prototipo e sottoporlo a test di lavaggio.

scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 3%.

colori

uniti e mélange

solidità

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

finissaggio industriale

vaporizzare abbondantemente in fase di stiro; per una mano più fluida e per eliminare le tensioni di smacchinatura, si consiglia un lavaggio con ammorbidente specifico.

servizio campionature fino al 30-06-2018

* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.***use***flat-knitting machine gauge 16-18 for 1-ply, 14 for 1-2 ply, gauge 12 for 2 ply, circular from 16 to 20 for 1-ply, cotton 24-27-30 gauge for 1-ply.**For 2 or more ply knitting, it is recommended to check machine tension.**Make and wash a prototype garment to evaluate shrinkage in the different knits.***knitting waste***the particular yarn construction and dyeing process cause a 3% knitting waste.***colours***solid and mélange***fastness***in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.***industrial finishing***steam generously during ironing; for a smoother hand and to eliminate the shrinkage due to the knitting tensions, it is suggested to wash with specific softener.***sampling service until 30-06-2018**

* colours ready for sampling

for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.