

E.Miroglio  
EAD Cert.N°  
SOF0170206  
ISO 9001:2008SAFE &  
healthy  
working  
conditionsNO harmful  
or irritant  
chemicals  
used**impiego**

macchina rettilinea su finezza 5 a 1 filo, 3 a 2 fili.  
Per valutare i cali nei vari punti maglia, è necessario eseguire un capo prototipo e sottoporlo a test di lavaggio.  
In fase di smacchinatura, porre particolare attenzione alla messa a punto della macchina, per limitare le rotture della piattina di poliestere.  
Per ottenere una superficie uniforme nei colori V6J, V6T, V3O, V3P, V3S, V3T, V4G, V4H, V4I, V4M, V4N, V4O, V4P, V4R, V4S, V4V, V4X, V4Y e V4Z si consiglia di lavorare il filato a più guidafile.

**scarto di lavorazione**

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 5-7%.

**colori**

uniti

**solidità**

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

**finissaggio industriale**

vaporizzare abbondantemente in fase di stiro; per una mano più fluida e per eliminare le tensioni di smacchinatura, si consiglia un lavaggio con ammorbidente specifico.

**servizio campionature fino al 30-06-2018**

\* colori pronti per campionatura

per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.

**use**

flat-knitting machine gauge 5 for 1-ply, 3 for 2 ply.  
Make and wash a prototype garment to evaluate shrinkage in the different knits.  
Pay great attention during knitting to the set-up of the machine, in order to limit the polyester breakage.  
When knitting V6J, V6T, V3O, V3P, V3S, V3T, V4G, V4H, V4I, V4M, V4N, V4O, V4P, V4R, V4S, V4W, V4X, V4Y and V4Z colors, it's advisable to use several threadguides to obtain a more uniform surface.

**knitting waste**

the particular yarn construction and dyeing process may cause a 5-7% knitting waste.

**colours**

solid

**fastness**

in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.

**industrial finishing**

steam generously during ironing; for a smoother hand and to eliminate the shrinkage due to the knitting tensions, it is suggested to wash with specific softener.

**sampling service until 30-06-2018**

\* colours ready for sampling

for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.

