

E.Miroglio  
EAD Cert.N°  
SOF0170206  
ISO 9001:2008



SAFE &  
healthy  
working  
conditions



NO harmful  
or irritant  
chemicals  
used

### impiego

macchina rettilinea su finezza 7 a 1 filo, 5 a 1 o 2 fili.  
Per valutare i cali nei vari punti maglia, è necessario eseguire un capo prototipo e sottoporlo a test di lavaggio.  
In fase di smacchinatura, porre particolare attenzione alla messa a punto della macchina, per limitare le rotture della piattina di poliestere.  
Per ottenere una superficie uniforme nei colori V3I, V3K e V3F si consiglia di lavorare il filato a più guidafili.

### scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 5-7%.

### colori

uniti

### solidità

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

### finissaggio industriale

vaporizzare abbondantemente in fase di stiro; per una mano più fluida e per eliminare le tensioni di smacchinatura, si consiglia un lavaggio con ammorbidente specifico.

### servizio campionature fino al 30-06-2018

\* colori pronti per campionatura

per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.

### use

flat-knitting machine gauge 7 for 1-ply, 5 for 1 or 2 ply.  
Make and wash a prototype garment to evaluate shrinkage in the different knits.

Pay great attention during knitting to the set-up of the machine, in order to limit the polyester breakage.

When knitting V3I, V3K and V3F colors, it's advisable to use several threadguides to obtain a more uniform surface.

### knitting waste

the particular yarn construction and dyeing process may cause a 5-7% knitting waste.

### colours

solid

### fastness

in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.

### industrial finishing

steam generously during ironing; for a smoother hand and to eliminate the shrinkage due to the knitting tensions, it is suggested to wash with specific softener.

### sampling service until 30-06-2018

\* colours ready for sampling

for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.

