

47% PC fibra acrilica / acrylic fibre
 44% CO cotone / cotton
 9% VI rayon viscosa / viscose rayon

knitted with Winknot-Lux Nm 5000 cod. 56164

E.Miroglio EAD
 ISO 14001:2015
 Cert. N°0039338
 ISO 9001:2015
 Cert. N°0039339



SAFE &
 healthy
 working
 conditions



NO harmful
 or irritant
 chemicals
 used

impiego

macchina rettilinea su finezza 5 a 1 filo.
 Per valutare i cali nei vari punti maglia, è necessario eseguire un capo prototipo e sottoporlo a test di lavaggio.
 Nei colori moulinè lavorare a più guidafili.

scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 5-7%.

colori

uniti e moulinè

solidità

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

finissaggio industriale

vaporizzare abbondantemente in fase di stiro; per una mano più fluida e per eliminare le tensioni di smacchinatura, si consiglia un lavaggio con ammorbidente specifico.

servizio campionature fino al 30-06-2019

* colori pronti per campionatura

per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.

use

*flat-knitting machine gauge 5 for 1-ply.
 Make and wash a prototype garment to evaluate shrinkage in the different knits.
 For moulinè colours, knit the yarn with several threadguides.*

knitting waste

the particular yarn construction and dyeing process may cause a 5-7% knitting waste.

colours

solid and moulinè

fastness

in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.

industrial finishing

steam generously during ironing; for a smo-other hand and to eliminate the shrinkage due to the knitting tensions, it is suggested to wash with specific softener.

sampling service until 30-06-2019

** colours ready for sampling*

for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.



OEKO-TEX®
 STANDARD 100
 05-2991-O CENTROSCOT
www.oeko-tex.com/standard/100

OEKO-TEX®
 STANDARD 100
 06-4222-O CENTROSCOT
www.oeko-tex.com/standard/100