



VISCOSE RAYON YARN – Dtex 333 /64f, 30f(flat)
RAW WHITE BRIGHT, DYED, DULL AND OPTICAL BLEACHED WHITE
IN CENTRIFUGAL METHOD

INDICATORS	SVILOTEX _{FIRST QUALITY}
1. Permissible deviation in the conditioned average linear density from nominal, %	+4 -3
2. Variation factor of linear density, %	Max 2,5
3. Specific dry breaking strength, cN/tex	Min 14,0
4. Dry breaking elasticity, %	18÷26
5. Number of twists over 1 m. filament	110±30
6. Sulphur content, %	Max 0,02
7. Number of knots on the upper face surface of the bobbin with conditional mass weight of 1000 g.	Max 5
8. Number of broken elementary filaments on the surface of the bobbin with conditional mass weight of 1000 g.	Max 12
9. Direction of the twist	S
10. Actual moisture content, %	6-14
11. Conditioned moisture content, %	13