

E.MIROGLIO EAD

Kv. Industrialen 8800 Sliven - BULGARIA
Tel (00359 44) 612423
Fax (00359 44) 612260 / 612274
e-mail: mirogl.io.lana@emirogl.io.com

1	ARTICLE	87619	AZALEASDES
1	LINE		LANA-WORSTED
1	TEXTILE	-	YARN DYED

08/08/2013

1 CONSTRUCTION CHARACTERISTICS

MATERIAL COMPOSITION	ISO 1833/5088	053	POLYESTER DISC.
		043	VIRGINWOOL
		004	ELASTANE
CONSTRUCTION			PLAIN WEAVE 1/1
WEIGHT G/MQ - G/ML	ISO 3801	186	285
TOT WIDTH MIN/MAX	CM ISO 22198	151	153
WORKING WIDTH MIN/MAX	CM ISO 22198	148	: 150
COUNT ENDS			TEX34,5SIRO+EL:DTEX 112 (56X2)
COUNT PICKS			TEX 34,5 SIRO+EL
THREADS WARP - WEFT	N/CM ISO 1049-2	22,2	: 22,7

1 FINISH CHARACTERISTICS

DYESTUFFS	DISPERSION-ACID DYES
FINISHING	SOFTENER

1 CARE LABELLING



1 MECHANICAL PROPERTIES

STRENGTH WARP / WEFT	N	ISO 13934-1	39	:	38
TENDENCY TO PILLING MARTINDALE (2000)		ISO 12945-2	3-4		
SEWING INSTR.NEEDLE SES N. STICH CM.			70	:	4-5

1 DIMENSIONAL STABILITY

			WARP%	WEFT%
SHRINKAGE HOFFMANN	DIN 53894-T2	-3,0	:	-3,0
SHRINKAGE WASCATOR 40 C	ISO 6330	-3,0	:	-3,0

1 COLOUR FASTNESS

			LIGHT	DARK
WASHING 40°C	ISO 105C06 AS2	4	:	3-4
PERSPIRATION ACID	ISO 105E04	4	:	3-4
PERSPIRATION ALKALINE	ISO 105E04	4	:	3-4
WATER 4 HOURS	ISO 105E01	4	:	3-4
RUBBING WET	ISO 105X12	4	:	3
RUBBING DRY	ISO 105X12	4	:	3

1 TRADE SPECIFIC INFORMATION

CUSTOM CODE	55151399000
OEKO-TEX CERTIFICATE	RDP 001772.0
WOOLMARK CERTIFICATE	0006BG00E

NOTES