

E.MIROGLIO EAD

Kv. Industrialen 8800 Sliven - BULGARIA
Tel (00359 44) 612423
Fax (00359 44) 612260 / 612274
e-mail: mirogl.io.lana@emirogl.io.com

1	ARTICLE	88954	SOLO
1	LINE		LANA-WORSTED
1	TEXTILE	-	YARN DYED

28/08/2013

1 CONSTRUCTION CHARACTERISTICS

MATERIAL COMPOSITION	ISO 1833/5088	064	VISCOSE
		034	POLYESTER DISC.
		002	ELASTANE
CONSTRUCTION			TWILL
WEIGHT G/MQ-G/ML	ISO 3801	203	290
TOT WIDTH MIN/MAX CM	ISO 22198	148	150
WORKING WIDTH MIN/MAX CM	ISO 22198	145	: 147
COUNT ENDS		TEX	19,66X1
COUNT PICKS		TEX	19,66+EL
THREADS WARP - WEFT N/CM	ISO 1049-2	43,6	: 37,7

1 FINISH CHARACTERISTICS

DYESTUFFS	DISPERSION-REACTIVE DYES
FINISHING	SOFTENER

1 CARE LABELLING



1 MECHANICAL PROPERTIES

STRENGTH WARP / WEFT N	ISO 13934-1	550	: 450
SLIDING SEAM WAR/WEF WEF/WAR 5MM KG	ISO 13936-1	17,0	: 17,0
TENDENCY TO PILLING MARTINDALE (2000)	ISO 12945-2	2	
SEWING INSTR.NEEDLE SES N. STICH CM.		70	: 3-4

1 DIMENSIONAL STABILITY

		WARP%	WEFT%
SHRINKAGE HOFFMANN	DIN 53894-T2	-3,0	: -3,0
SHRINKAGE WASCATOR 40 C	ISO 6330	-3,0	: -3,0

1 COLOUR FASTNESS

		LIGHT	DARK
WASHING 40°C	ISO 105C06 AS2	4	: 3-4
PERSPIRATION ACID	ISO 105E04	4	: 3-4
PERSPIRATION ALKALINE	ISO 105E04	4	: 3-4
WATER 4 HOURS	ISO 105E01	4	: 3-4
RUBBING WET	ISO 105X12	4	: 3
RUBBING DRY	ISO 105X12	4	: 3

1 TRADE SPECIFIC INFORMATION

CUSTOM CODE	55151399000
OEKO-TEX CERTIFICATE	RDP 001772.0

NOTES