

E.MIROGLIO EAD

Kv. Industrialen 8800 Sliven - BULGARIA
Tel (00359 44) 612423
Fax (00359 44) 612260 / 612274
e-mail: mirogl.io.lana@emirogl.io.com

1	ARTICLE	89146	STILTON
1	LINE		LANA-WORSTED
1	TEXTILE	-	YARN DYED

28/08/2013

1 CONSTRUCTION CHARACTERISTICS

MATERIAL COMPOSITION	ISO 1833/5088	063	POLYESTER DISC.
		035	VISCOSE
		002	ELASTANE
CONSTRUCTION			SATEEN
WEIGHT G/MQ-G/ML	ISO 3801	240	360
TOT WIDTH MIN/MAX CM	ISO 22198	148	150
WORKING WIDTH MIN/MAX CM	ISO 22198	145	: 147
COUNT ENDS		TEX	19,66
COUNT PICKS		TEX	19,66 CORE
THREADS WARP - WEFT	N/CM	ISO 1049-2	62,4 : 39,4

1 FINISH CHARACTERISTICS

DYESTUFFS	DISPERSION-REACTIVE DYES
FINISHING	SOFTENER

1 CARE LABELLING



1 MECHANICAL PROPERTIES

STRENGTH WARP / WEFT	N	ISO 13934-1	950 : 500
SLIDING SEAM WAR/WEF WEF/WAR	5MM KG	ISO 13936-1	18,0 : 18,0
TENDENCY TO PILLING MARTINDALE (2000)		ISO 12945-2	2-3
SEWING INSTR.NEEDLE SES N. STICH CM.			70___ : 3-4

1 DIMENSIONAL STABILITY

		WARP% WEFT%
SHRINKAGE HOFFMANN	DIN 53894-T2	-3,0 : -3,0
SHRINKAGE WASCATOR 40 C	ISO 6330	-3,0 : -3,0

1 COLOUR FASTNESS

		LIGHT	DARK
WASHING 40°C	ISO 105C06 AS2	4	: 3-4
PERSPIRATION ACID	ISO 105E04	4	: 3-4
PERSPIRATION ALKALINE	ISO 105E04	4	: 3-4
WATER 4 HOURS	ISO 105E01	4	: 3-4
RUBBING WET	ISO 105X12	4	: 3
RUBBING DRY	ISO 105X12	4	: 3

1 TRADE SPECIFIC INFORMATION

CUSTOM CODE	55151399000
OEKO-TEX CERTIFICATE	RDP 001772.0

NOTES