

E.MIROGLIO EAD

Kv. Industrialen 8800 Sliven - BULGARIA
Tel (00359 44) 612423
Fax (00359 44) 612260 / 612274
e-mail: mirogl.io.lana@emirogl.io.com

1	ARTICLE	86406	LEADER
1	LINE		LANA-WORSTED
1	TEXTILE	-	YARN DYED

09/08/2013

1 CONSTRUCTION CHARACTERISTICS

MATERIAL COMPOSITION	ISO 1833/5088	053	POLYESTER DISC.
		043	VIRGINWOOL
		004	ELASTANE
CONSTRUCTION			SERGE OF 3
WEIGHT G/MQ - G/ML	ISO 3801	229	350
TOT WIDTH MIN/MAX	CM ISO 22198	151	153
WORKING WIDTH MIN/MAX	CM ISO 22198	148	: 150
COUNT ENDS		TEX 34.5	SIRO
COUNT PICKS		TEX 34.5	SIRO
THREADS WARP - WEFT	N/CM ISO 1049-2	26,7	: 28,9

1 FINISH CHARACTERISTICS

DYESTUFFS	DISPERSION-ACID DYES
FINISHING	SOFTENER

1 CARE LABELLING



1 MECHANICAL PROPERTIES

TENDENCY TO PILLING MARTINDALE (2000)	ISO 12945-2	3-4	
SEWING INSTR.NEEDLE SES N. STICH CM.		70	: 4-5
ABRASION RESISTENCE MARTINDALE	EN ISO 12947-2	40000	TURNS

1 DIMENSIONAL STABILITY

		WARP%	WEFT%
SHRINKAGE HOFFMANN	DIN 53894-T2	-3,0	: -3,0
SHRINKAGE WASCATOR 40 C	ISO 6330	-2,0	: -2,0

1 COLOUR FASTNESS

		LIGHT	DARK
WASHING 40°C	ISO 105C06 AS2	4	: 3-4
PERSPIRATION ACID	ISO 105E04	4	: 3-4
PERSPIRATION ALKALINE	ISO 105E04	4	: 3-4
WATER 4 HOURS	ISO 105E01	4	: 3-4
RUBBING WET	ISO 105X12	4	: 3
RUBBING DRY	ISO 105X12	4	: 3

1 TRADE SPECIFIC INFORMATION

CUSTOM CODE	55151399000
OEKO-TEX CERTIFICATE	RDP 001772.0
WOOLMARK CERTIFICATE	0006BG00E

NOTES