

E.MIROGLIO EAD

Kv. Industrialen 8800 Sliven - BULGARIA
Tel (00359 44) 612423
Fax (00359 44) 612260 / 612274
e-mail: mirogl.io.lana@emirogl.io.com

1	ARTICLE	86995	TALAS NEW
1	LINE		LANA-WORSTED
1	TEXTILE	-	YARN DYED

09/08/2013

1 CONSTRUCTION CHARACTERISTICS

MATERIAL COMPOSITION	ISO 1833/5088	054	POLYESTER DISC.
		044	VIRGINWOOL
		002	ELASTANE
CONSTRUCTION			SATEEN
WEIGHT G/MQ-G/ML	ISO 3801	228	330
TOT WIDTH MIN/MAX	CM ISO 22198	143	145
WORKING WIDTH MIN/MAX	CM ISO 22198	140	: 143
COUNT ENDS		TEX 33,3	SIRO
COUNT PICKS		TEX 29	CORE
THREADS WARP - WEFT	N/CM ISO 1049-2	33,9	: 30,3

1 FINISH CHARACTERISTICS

DYESTUFFS	DISPERSION-ACID DYES
FINISHING	SOFTENER

1 CARE LABELLING



1 MECHANICAL PROPERTIES

STRENGTH WARP / WEFT	N	ISO 13934-1	650	:	450
SLIDING SEAM WAR/WEF WEF/WAR	5MM KG	ISO 13936-1	15,0	:	17,0
TENDENCY TO PILLING MARTINDALE (2000)	ISO 12945-2	3			
SEWING INSTR.NEEDLE SES N. STICH CM.		70	:	4-5	

1 DIMENSIONAL STABILITY

		WARP% WEFT%			
SHRINKAGE HOFFMANN	DIN 53894-T2	-3,0	:	-3,0	
SHRINKAGE WASCATOR 40 C	ISO 6330	-2,0	:	-2,0	

1 COLOUR FASTNESS

		LIGHT	DARK		
WASHING 40°C	ISO 105C06 AS2	4	:	3-4	
PERSPIRATION ACID	ISO 105E04	4	:	3-4	
PERSPIRATION ALKALINE	ISO 105E04	4	:	3-4	
WATER 4 HOURS	ISO 105E01	4	:	3-4	
RUBBING WET	ISO 105X12	4	:	3	
RUBBING DRY	ISO 105X12	4	:	3	

1 TRADE SPECIFIC INFORMATION

CUSTOM CODE	55151399000
OEKO-TEX CERTIFICATE	RDP 001772.O
WOOLMARK CERTIFICATE	0006BG00E

NOTES