



by EDOARDO MIROGLIO

E.Miroglio EAD  
ISO 14001:2015  
Cert. N°0039338  
ISO 9001:2015  
Cert. N°0039339SAFE &  
healthy  
working  
conditionsNO harmful  
or irritant  
chemicals  
used**impiego**

macchina rettilinea su finezza 7 e 5 a 1 filo

**estensibilità e restringimento**

il grado d'elasticità del capo è determinato dalla regolazione della tensione del filo e della fittezza dei punti maglia in fase di smacchinatura. Si consiglia di eseguire un capo prototipo e sottoporlo ad un test di lavaggio.

**scarto di lavorazione**

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 5-7%.

**colori**

uniti

**solidità**

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

**finissaggio industriale**

per scaricare le tensioni di lavorazione e completare il ritorno elastico della componente Elastan, si consiglia di lavare con ammorbidente specifico e vaporizzare abbondantemente in fase di stiro.

**servizio campionature fino al 31-12-2020**

\* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.***use***flat-knitting machine gauge 7-5 for 1-ply.***stretch and shrinking degree***the garment stretch degree is determined by yarn tension and knit thickness adjustment during knitting. It is suggested to make a prototype garment and wash it as a test.***knitting waste***the particular yarn construction and dyeing process may cause a 5-7% knitting waste.***colours***solid***fastness***in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.***industrial finishing***in order to loosen the knitting tensions and help the Elastan component stretch return, it is suggested to wash with specific softener and steam generously during ironing.***sampling service until 31-12-2020**

\* colours ready for sampling

*for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.*