

Cod. 54547

# Fleecy

Nm 6000

57% PA poliammide / polyamide  
43% VI viscosa / viscose

W  
22  
23



by EDUARDO MIROGLIO

E.Miroglio EAD  
ISO 14001:2015  
Cert. N°0039338  
ISO 9001:2015  
Cert. N°0039339



SAFE &  
healthy  
working  
conditions



NO harmful  
or irritant  
chemicals  
used

## impiego

macchina rettilinea su finezza 5 a 1 filo.

## estensibilità e restringimento

il grado d'elasticità del capo è determinato dalla regolazione della tensione del filo e della fittezza dei punti maglia in fase di smacchinatura. Si consiglia di eseguire un capo prototipo e sottoporlo ad un test di lavaggio.

## scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 5-7%.

## colori

uniti e mélange.

## solidità

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

## finissaggio industriale

per scaricare le tensioni di lavorazione e completare il ritorno elastico della componente poliammidica, si consiglia di lavare con ammorbidente specifico e vaporizzare abbondantemente in fase di stiro.

## servizio campionature fino al 31-12-2021

\* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.*

## use

flat- knitting machine gauge 5 for 1 ply.

## stretch and shrinking degree

*the garment stretch degree is determined by yarn tension and knit thickness adjustment during knitting. It is suggested to make a prototype garment and wash it as a test.*

## knitting waste

*the particular yarn construction and dyeing process may cause a 5-7% knitting waste.*

## colours

solid and mélange.

## fastness

*in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.*

## industrial finishing

*in order to loosen the knitting tensions and help the polyamide component stretch return, it is suggested to wash with specific softener and steam generously during ironing.*

## sampling service until 31-12-2021

\* colours ready for sampling

*for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.*

•1 bianco *white* •2 chiari *light* •3 medi *medium* •4 scuri *dark* •5 special *special*

