



impiego

macchina rettilinea su finezza 12-14 a 1 filo,  
circolare da 12 a 20 a 1 filo, cotton 21-24  
a 1 filo.

estensibilità e restringimento

il grado d’elasticità del capo è determina-  
to dalla regolazione della tensione del filo  
e della fittezza dei punti maglia in fase di  
smacchinatura. Si consiglia di eseguire un  
capo prototipo e sottoporlo ad un test di  
lavaggio.

scarto di lavorazione

la particolare costruzione di quest’articolo  
e il processo di tintura comportano uno  
scarto del 5-7%.

colori

uniti

solidità

secondo le norme UNI/ISO; per i rigati  
con colori contrastanti, è necessario  
richiedere solidità specifiche ed eseguire  
test di lavaggio.

finissaggio industriale

per scaricare le tensioni di lavorazione e  
completare il ritorno elastico della com-  
ponente poliestere, si consiglia di lavare  
con ammorbidente specifico e vaporizzare  
abbondantemente in fase di stiro.

colori a Stock Service

001-002-066-099-3K3-5R6-5X5-5R1

per informazioni sull’utilizzo dell’artico-  
lo e dei bagni ottimali di tintura, vi pre-  
ghiamo di richiedere la scheda tecnica.

Stock Service

use

flat-knitting machine gauge 12-14 for 1-ply,  
circular from 12 to 20 for 1-ply, cotton  
21-24 for 1-ply.

stretch and shrinking degree

the garment stretch degree is determined by  
yarn tension and knit thickness adjustment  
during knitting. It is suggested to make a  
prototype garment and wash it as a test.

knitting waste

the particular yarn construction  
and dyeing process may cause a  
5-7% knitting waste.

colours

solid

fastness

in compliance with UNI/ISO norms; for  
striped garments with contrasting colours,  
it is recommended to ask for specific  
fastness and carry out washing tests.

industrial finishing

in order to loosen the knitting tensions  
and help the polyester component stretch  
return, it is suggested to wash with specific  
softener and steam generously during  
ironing.

Stock Service colours

001-002-066-099-3K3-5R6-5X5-5R1

for any information regarding the use  
and dye-lot sizes of the yarn please ask  
for the technical sheet.

|    |         |         |
|----|---------|---------|
| •1 | bianco  | white   |
| •2 | chiari  | light   |
| •3 | medi    | medium  |
| •4 | scuri   | dark    |
| •5 | special | special |



NO harmful or irritant  
chemicals used.  
NON trattato con sostanze  
nocive o irritanti.



Safe & healthy  
working conditions.  
Condizioni di lavoro  
sane e sicure.

