



impiego

macchina rettilinea su finezza 5 a 1 filo,
3 a 2 fili.

colori

uniti, mélange.
Non sono riproducibili colori a campione

solidità

secondo le norme UNI/ISO; per i rigati
con colori contrastanti, è necessario
richiedere solidità specifiche ed eseguire
test di lavaggio.

finissaggio industriale

vaporizzare abbondantemente in fase di
stiro. Per ottenere una mano più gonfia e
quindi una maglia più curata, è consigliabile
un lavaggio con un minimo di ammorbiden-
te specifico.

tutti i colori sono pronti per campionatura

*per informazioni sull'utilizzo dell'artico-
lo e dei bagni ottimali di tintura, vi pre-
ghiamo di richiedere la scheda tecnica.*

use

*flat-knitting machine gauge 5 for 1-ply,
3 for 2-ply.*

colours

*solid, mélange.
We cannot match colours in this quality.*

fastness

*in compliance with UNI/ISO norms;
for striped garments with contrasting
colours, it is recommended to ask for
specific fastness and carry out washing tests.*

industrial finishing

*steam generously during ironing.
Wash with a minimum dose of appropriate
softener for a more voluminous touch and a
cleaner feel.*

all colours are ready for sampling

*for any information regarding the use
and dye-lot sizes of the yarn please ask
for the technical sheet.*

