



**impiego**

macchina rettilinea su finezza 12 a 1 filo,  
circolare da 12 a 20 a 1 filo, cotton 21  
a 1 filo.

**estensibilità e restringimento**

il grado d’elasticità del capo è determinato  
dalla regolazione della tensione del filo  
e della fittezza dei punti maglia in fase  
di smacchinatura. Si consiglia di eseguire  
un capo prototipo e sottoporlo ad un  
test di lavaggio.

**scarto di lavorazione**

la particolare costruzione di quest’articolo e  
il processo di tintura comportano uno scarto  
del 5-7%.

**colori**

uniti e mélange.

**solidità**

secondo le norme UNI/ISO; per i rigati  
con colori contrastanti, è necessario  
richiedere solidità specifiche ed eseguire  
test di lavaggio.

**finissaggio industriale**

per scaricare le tensioni di lavorazione  
e completare il ritorno elastico della  
componente elasthan, si consiglia di lavare  
con ammorbidente specifico e vaporizzare  
abbondantemente in fase di stiro.

**servizio campionature fino al 31-12-2013**

\* colori pronti per campionatura

*per informazioni sull’utilizzo dell’articolo  
e dei bagni ottimali di tintura, vi pre-  
ghiamo di richiedere la scheda tecnica.*

**use**

*flat-knitting machine gauge 12 for 1-ply,  
circular from 12 to 20 for 1-ply, cotton  
21 for 1-ply.*

**stretch and shrinking degree**

*the garment stretch degree is determined by  
yarn tension and knit thickness adjustment  
during knitting. It is suggested to make a  
prototype garment and wash it as a test.*

**knitting waste**

*the particular yarn construction and dyeing  
process may cause a 5-7% knitting waste.*

**colours**

*solid and mélange.*

**fastness**

*in compliance with UNI/ISO norms;  
for striped garments with contrasting  
colours, it is recommended to ask for  
specific fastness and carry out washing tests.*

**industrial finishing**

*in order to loosen the knitting tensions and  
help the elasthan component stretch return,  
it is suggested to wash with specific softener  
and steam generously during ironing.*

**sampling service until 31-12-2013**

\* colours ready for sampling

*for any information regarding the use  
and dye-lot sizes of the yarn please ask  
for the technical sheet.*

|    |         |         |
|----|---------|---------|
| •1 | bianco  | white   |
| •2 | chiari  | light   |
| •3 | medi    | medium  |
| •4 | scuri   | dark    |
| •5 | special | special |

