

**Enchant / Enchant-one**

Nm 3000

Nm 3000



by EDUARDO MIROGLIO

**Enchant**

93% VI rayon viscosa / viscose rayon  
4% PL poliestere metallizzato / metallized polyester  
3% PA fibra poliammidica / polyamide fibre

**Enchant-one**

100% VI rayon viscosa / viscose rayon

**impiego**

macchina rettilinea su finezza 3 a 1 filo,  
Per valutare i cali nei vari punti maglia,  
è necessario eseguire un capo prototipo  
e sottoporlo a test di lavaggio.  
In fase di smacchinatura, porre particolare  
attenzione alla messa a punto della  
macchina, per limitare le rotture della  
piattina di poliestere.

**scarto di lavorazione**

la particolare costruzione di quest'articolo  
e il processo di tintura comportano uno  
scarto del 5-7%.

**colori**

moulinè

**solidità**

secondo le norme UNI/ISO; per i rigati  
con colori contrastanti, è necessario  
richiedere solidità specifiche ed eseguire  
test di lavaggio.

**finissaggio industriale**

vaporizzare abbondantemente in fase  
di stiro; per una mano più fluida e per  
eliminare le tensioni di smacchinatura, si  
consiglia un lavaggio con ammorbidente  
specifico.

**servizio campionature fino al 30-06-2016**

\* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo  
e dei bagni ottimali di tintura, vi pre-  
ghiamo di richiedere la scheda tecnica.*

**use**

*flat-knitting machine gauge 3 for 1-ply.  
In order to evaluate shrinkage in the  
different knits, it is suggested to make a  
prototype garment and wash it as a test.  
Pay great attention during knitting to the  
set-up of the machine, in order to limit the  
polyester breakage.*

**knitting waste**

*the particular yarn construction and  
dyeing process may cause a 5-7%  
knitting waste*

**colours**

moulinè

**fastness**

*in compliance with UNI/ISO norms; for  
striped garments with contrasting colours,  
it is recommended to ask for specific  
fastness and carry out washing tests.*

**industrial finishing**

*steam generously during ironing; for  
a smoother hand and to eliminate the  
shrinkage due to the knitting tensions,  
it is suggested to wash with specific  
softener.*

**sampling service until 30-06-2016**

\* colours ready for sampling

*for any information regarding the use  
and dye-lot sizes of the yarn please ask  
for the technical sheet.*

