



94% VI rayon viscosa FSC® / FSC® rayon viscosa
6% PL poliestere elasticizzato / stretch polyester



by EDUARDO MIROGLIO

E.Miroglio EAD

ISO 14001:2015

Cert. N° BG.121922E/U

ISO 9001:2015

Cert. N° BG.121922Q/U

SAFE &
healthy
working
conditionsNO harmful
or irritant
chemicals
used**impiego**

macchina rettilinea su finezza 16 e 14 a 1 filo, cotton
24-27 gauge a 1 filo.

estensibilità e restringimento

il grado d'elasticità del capo è determinato dalla regolazio-
ne della tensione del filo e della fittezza dei punti maglia
in fase di smacchinatura. Si consiglia di eseguire un capo
prototipo e sottoporlo ad un test di lavaggio.

scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di
tintura comportano uno scarto del 5-7%.

colori

uniti

solidità

secondo le norme UNI/ISO; per i rigati con colori
contrastanti, è necessario richiedere solidità specifiche
ed eseguire test di lavaggio.

finissaggio industriale

per scaricare le tensioni di lavorazione e completare il
ritorno elastico della componente poliestere, si consiglia
di lavare con ammorbidente specifico e vaporizzare abbon-
dantemente in fase di stiro.

servizio campionature fino al 30-06-2023

* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo e dei bagni
ottimali di tintura, vi preghiamo di richiedere la
scheda tecnica.*

use

*flat-knitting machine gauge 16-14 for 1-ply, cotton
24-27 gauge for 1-ply.*

stretch and shrinking degree

*the garment stretch degree is determined by yarn tension
and knit thickness adjustment during knitting. It is sug-
gested to make a prototype garment and wash it as a test.*

knitting waste

*the particular yarn construction and dyeing process may
cause a 5-7% knitting waste.*

colours

solid

fastness

*in compliance with UNI/ISO norms; for striped garments
with contrasting colours, it is recommended to ask for
specific fastness and carry out washing tests.*

industrial finishing

*in order to loosen the knitting tensions and help the
polyester component stretch return, it is suggested to
wash with specific softener and steam generously
during ironing.*

sampling service until 30-06-2023

* colours ready for sampling

*for any information regarding the use and dye-lot
sizes of the yarn please ask for the technical sheet.*

