



by EDUARDO MIROGLIO

E.Miroglio EAD  
ISO 14001:2015  
Cert. N°0039338  
ISO 9001:2015  
Cert. N°0039339



SAFE &  
healthy  
working  
conditions



NO harmful  
or irritant  
chemicals  
used

### impiego

macchina rettilinea su finezza 12-14 a 1 filo, 7 a 2 fili,  
circolare da 12 a 20 a 1 filo, cotton 21-24 gauge a 1 filo.

### estensibilità e restringimento

il grado d'elasticità del capo è determinato dalla  
regolazione della tensione del filo e della fittezza dei punti  
maglia in fase di smacchinatura. Si consiglia di eseguire un  
capo prototipo e sottoporlo ad un test di lavaggio.

### scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di  
tintura comportano uno scarto del 5-7%.

### colori

uniti

### solidità

secondo le norme UNI/ISO; per i rigati con colori  
contrastanti, è necessario richiedere solidità specifiche  
ed eseguire test di lavaggio.

### finissaggio industriale

per scaricare le tensioni di lavorazione e completare il  
ritorno elastico della componente poliestere, si consiglia  
di lavare con ammorbidente specifico e vaporizzare  
abbondantemente in fase di stiro.

### servizio campionature fino al 31-12-2020

\* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo e dei bagni  
ottimali di tintura, vi preghiamo di richiedere la  
scheda tecnica.*

### use

*flat-knitting machine gauge 12-14 for 1-ply, 7 for 2 ply cir-  
cular from 12 to 20 for 1-ply, cotton 21-24 gauge for 1-ply.*

### stretch and shrinking degree

*the garment stretch degree is determined by yarn tension  
and knit thickness adjustment during knitting. It is sug-  
gested to make a prototype garment and wash it as a test.*

### knitting waste

*the particular yarn construction and dyeing process may  
cause a 5-7% knitting waste.*

### colours

solid

### fastness

*in compliance with UNI/ISO norms; for striped garments  
with contrasting colours, it is recommended to ask for  
specific fastness and carry out washing tests.*

### industrial finishing

*in order to loosen the knitting tensions and help the  
polyester component stretch return, it is suggested to  
wash with specific softener and steam generously  
during ironing.*

### sampling service until 31-12-2020

\* colours ready for sampling

*for any information regarding the use and dye-lot  
sizes of the yarn please ask for the technical sheet.*

